

**Tepex® dynalite 111-RG600(x)/47%**  
**Roving Glass - HDPE Consolidated Composite Laminate**

| Layup                         | Test Condition | According to Standard | Unit              | Value                            |             |
|-------------------------------|----------------|-----------------------|-------------------|----------------------------------|-------------|
|                               |                |                       |                   | Longitudinal                     | Transversal |
| Fiber                         | -              | -                     | -                 | E-Glass Roving                   |             |
| Weaving style                 | -              | DIN ISO 9354          | -                 | Twill 2/2                        |             |
| Area weight (dry fabric)      | -              | DIN EN 12127          | g/m <sup>2</sup>  | 600                              |             |
| Yarn                          | -              | DIN EN 12654-2/3      | tex               | 1200                             |             |
| Yarn density                  | -              | DIN EN 1049-2         | 1/cm              | 2.5                              | 2.5         |
| Weight rate                   | -              | -                     | %                 | 50                               | 50          |
| Polymer                       | -              | -                     | -                 | High Density Polyethylene (HDPE) |             |
| Fiber content (nominal)       | -              | -                     | vol.-%            | 47                               |             |
| Thickness per layer (nominal) | -              | -                     | mm                | 0.5                              |             |
| Laminate density              | -              | ISO 1183-1            | g/cm <sup>3</sup> | 1.71                             |             |

| Mechanical properties       | Test Condition | According to Standard     | Unit | Value |
|-----------------------------|----------------|---------------------------|------|-------|
| Tensile modulus             | 23 °C, dry     | ISO 527-4/5 <sup>1)</sup> | GPa  | 18    |
| Tensile strength            | 23 °C, dry     | ISO 527-4/5 <sup>1)</sup> | MPa  | 310   |
| Tensile elongation at break | 23 °C, dry     | ISO 527-4/5 <sup>1)</sup> | %    | 2.1   |
| Flexural modulus            | 23 °C, dry     | ISO 14125 <sup>2)</sup>   | GPa  | 12    |
| Flexural strength           | 23 °C, dry     | ISO 14125 <sup>2)</sup>   | MPa  | 150   |

| Thermal properties                                 | Test Condition | According to Standard | Unit | Value |
|--|----------------|-----------------------|------|-------|
| Melting temperature                                | 10 K/min       | ISO 11357-3           | °C   | 129   |
| Heat deflection temperature (matrix) <sup>4)</sup> | 0.45 MPa       | ISO 75-1/-2           | °C   | 82    |

**Tepex® dynalite 111-RG600(x)/47%**  
**Roving Glass - HDPE Consolidated Composite Laminate****Legend**

- : Not relevant  
dry: dry as manufactured  
1) Test specimen (250 x 25 x 2) mm  
2) Test specimen (80 x 25) mm  
4) Based on ISO 75-1/-2

® Bond-Laminates registered trademark

The values in the datasheet are for this specific composition only, the characteristics of composites depend on the reinforcement level and the fiber orientation. Non-standard thickness may also alter some or all of these properties. The data listed here fall within the normal range of product properties, but they should not be used to establish specification limits nor used alone as basis of design. The underlying tests were conducted at room temperature.

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided - especially that contained in our safety data and technical information sheets - and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold and our advisory service is given in accordance with the current version of our General Conditions of Sale and Delivery.

Caution: Do not use this product in medical applications involving permanent implantation in human body.